

NORMY ZAKŁADOWE Z DNIA 31.08.2012r.- wytyczne szczegółowe.

Produkt	MgO		CaO	Strata prażenia	SiO ₂	Fe ₂ O ₃	Al ₂ O ₃	H ₂ O
	Forma węglanowa	Forma węglanowo - krzemianowa						
MAGNEZYT MIELONY R-30	min. 20	≤ 30	< 3,5	<27	<38	<10	<3,0	< 10,0
MAGNEZYT MIELONY R-35	min. 30	≤ 35	< 3,0	<30	<38	<10	<3,0	< 10,0
MAGNEZYT MIELONY R-35W	min. 35	> 35	< 3,0	<40	<25	<7,0	<2,0	< 10,0
MAGNEZYT MIELONY R-40	min. 38	≤ 40	< 2,5	<47%	<18	<4,0	<1,5	< 9,0
MAGNEZYT SUROWY MIELONY	min. 40	≤ 43	< 2,0	<48	<16	<4,0	<1,0	< 8,0
MAGNEZYT SUROWY KRUSZONY	min. 40	≤ 43	< 2,0	<48	>4,0	<5,0	<1,0	< 8,0
MAGNEZYT SUROWY KRUSZONY- EXTRA	min. 42	≤ 45	< 1,5	<50	<8,0	<3,0	<1,0	< 6,0

NORMA ZAKŁADOWA Z DNIA 28.04.2009r

TLENEK MAGNEZU	min. 80		1-3	max. 4
-----------------------	---------	--	-----	--------

%MgO	30	40	45	84,5	86	88	90	91	94
%Mg	18	24	27,1	51	51,86	53,07	54,27	54,88	56,68
%MgCO ₃	62,8	83,7	94,1						